

DELPHION

Log Out

Work Files

Saved Searches

RESEARCH

PRODUCTS

INSIDE DELPHION

My Account

Search: Quick/Number Boolean Advanced Derwent

Help

No active trail

Select

Stop Tracking

The Delphion Integrated View: INPADOC Record

Get Now: ☒ PDF | File History | Other choices

Tools: Add to Work File: Create new Work File

View: Jump to: Top ☒ Email this to a friend

Title: HU0001904AB: SUSPENSIONS WITH HIGH STORAGE STABILITY, COMPRISING AN AQUEOUS SILICATE SOLUTION AND A FILLER MATERIAL, COMPOSITIONS CONTAINING THEREOF AND USING

Derwent Title: Suspension with high storage stability useful e.g. as drilling fluid - comprises aqueous silicate solution and a filler material which is zeolites, fine particulates of amorphous alkali metal aluminosilicate and or graphite or carbon black [Derwent Record]

Country: HU Hungary
Kind: AB Publ. of Application without search report
Inventor: HOWARTH, IAN MAURICE; United Kingdom
OSINGA, THEO JAN; Netherlands
Assignee: OSINGA, THEO JAN Netherlands
News, Profiles, Stocks and More about this company

Published / Filed: 2000-11-28 / 1998-04-27

Application Number: HU2000000001904

IPC Code: IPC-7: C04B 14/04; C04B 22/00; C04B 22/06; C04B 28/26; C09J 1/02; C09K 7/04; C09K 17/12; D21H 17/63;

ECLA Code: None

Priority Number: 1997-04-30 GB1997000008831
1998-04-27 WO1998GB0001226

INPADOC Legal Status: None Get Now: Family Legal Status Report

Designated Country: AL AM AP AZ BA BB BG BY CA CU CZ EA EE GE GH GM GW HU ID IL IS JP KE AT BE CH CY DE DK ES FI FR GR IE IT




Family:

PDF	Publication	Pub. Date	Filed	Title
<input checked="" type="checkbox"/>	ZA9902113A	1999-11-01	1999-03-16	HARDENER FOR HARDENING SILICATE SOLUTIONS.
<input checked="" type="checkbox"/>	ZA9803696A	1999-11-01	1998-04-30	HARDENER FOR HARDENING SILICATE SOLUTIONS.
<input checked="" type="checkbox"/>	ZA9803695A	1999-11-01	1998-04-30	ADHESIVE COMPOSITION.
<input checked="" type="checkbox"/>	ZA9803694A	1999-11-01	1998-04-30	ZEOLITE A24 (SUSPENSION WITH HIGH STORAGE STABILITY).
<input checked="" type="checkbox"/>	WO9849118A1	1998-11-05	1998-04-27	HARDENER FOR HARDENING SILICATE SOLUTIONS
<input checked="" type="checkbox"/>	WO9849117A1	1998-11-05	1998-04-27	ADHESIVE COMPOSITION
<input checked="" type="checkbox"/>	WO9849116A1	1998-11-05	1998-04-27	SUSPENSIONS WITH HIGH STORAGE STABILITY, COMPRISING AN AQUEOUS SILICATE SOLUTION AND A FILLER MATERIAL
<input checked="" type="checkbox"/>	US6372694	2002-04-16	1999-10-27	Suspensions with high storage stability, comprising an aqueous silicate solution and a filler material
<input checked="" type="checkbox"/>	TW0438872B	2001-06-07	1998-04-29	ADHESIVE COMPOSITION
<input checked="" type="checkbox"/>	PL0336584A1	2000-07-03	1998-04-27	SUSPENSIONS OF HIGH STORAGE STABILITY CONTAINING AQUEOUS SILICATE SOLUTION AND A FILTER
<input checked="" type="checkbox"/>	JP2001527592T2	2001-12-25	1998-04-27	
<input checked="" type="checkbox"/>	JP2001522395T2	2001-11-13	1998-04-27	
<input checked="" type="checkbox"/>	ID0023929A	2000-05-25	1998-04-27	SUSPENSİ-SUSPENSİ DENGAN STABILITAS PENYIMPANAN YANG TINGGI, YANG MENGANDUNG LARUTAN SILIKAT BERAIR DAN BAHAN PENGISI
<input checked="" type="checkbox"/>	ID0022970A	1999-12-23	1998-04-27	KOMPOSISI PEREKAT
<input checked="" type="checkbox"/>	HU0001904AB	2000-11-28	1998-04-27	SUSPENSIONS WITH HIGH STORAGE STABILITY, COMPRISING AN AQUEOUS SILICATE SOLUTION AND A FILLER MATERIAL, COMPOSITIONS CONTAINING THEREOF AND USING
	GB9708831A0	1997-06-25		
<input checked="" type="checkbox"/>	EP1025060A1	2000-08-09	1998-04-27	HARDENER FOR HARDENING SILICATE SOLUTIONS
<input checked="" type="checkbox"/>	EP0991608A1	2000-04-12	1998-04-27	ADHESIVE COMPOSITION
<input checked="" type="checkbox"/>	EP0991607B1	2001-10-10	1998-04-27	SUSPENSIONS WITH HIGH STORAGE STABILITY, COMPRISING AN AQUEOUS SILICATE SOLUTION AND A FILLER MATERIAL
<input checked="" type="checkbox"/>	EP0991607A1	2000-04-12	1998-04-27	SUSPENSIONS WITH HIGH STORAGE STABILITY, COMPRISING AN AQUEOUS SILICATE SOLUTION AND A FILLER MATERIAL
<input checked="" type="checkbox"/>	DE69801995T2	2002-04-04	1998-04-27	WAESSRIGE SILIKATLOESUNG UND FUELLSTOFF ENTHALTENDE SUSPENSIONEN MIT HOHER LAGERSTABILITAET
	DE69801995C0	2001-11-15	1998-04-27	WAESSRIGE SILIKATLOESUNG UND FUELLSTOFF ENTHALTENDE SUSPENSIONEN MIT HOHER LAGERSTABILITAET


<input checked="" type="checkbox"/>	CN1261335T	2000-07-26	1998-04-27	Suspensions with high storage stability, comprising an aqueous silicate solution and a filler material
<input checked="" type="checkbox"/>	CN1261335A	2000-07-26	1998-04-27	Suspensions with high storage stability, comprising an aqueous silicate solution and a filler material
<input checked="" type="checkbox"/>	CN1253536T	2000-05-17	1998-04-27	Adhesive composition
<input checked="" type="checkbox"/>	CN1253536A	2000-05-17	1998-04-27	Adhesive composition
<input checked="" type="checkbox"/>	CA2286005AA	1998-11-05	1998-04-27	SUSPENSIONS WITH HIGH STORAGE STABILITY, COMPRISING AN AQUEOUS SILICATE SOLUTION AND A FILLER MATERIAL
<input checked="" type="checkbox"/>	CA2285994AA	1998-11-05	1998-04-27	ADHESIVE COMPOSITION
<input checked="" type="checkbox"/>	BR9809383A	2000-07-04	1998-04-27	SUSPENSÃO, FLUIDOS DE PERFURAR E DE RENOVACAO DE ESGOTO, COMPOSICOES ADESIVA, AGLUTINANTE, DE FIXACAO DE RESIDUOS, DE FIXACAO E ENDURECIMENTO PARA SUPERFICIES DE BASE, DE CIMENTO DE CONCRETO PARA CONSTRUCAO, DE REVESTIMENTO POR PULVERIZACAO, DE CARGA DE PAPEL, E, USOS DE UMA COMPOSICAO ADESIVA, DE UM SISTEMA ENDURECEDOR E DE UMA SILICA AMORFA COMO
<input checked="" type="checkbox"/>	BR9809340A	2000-07-04	1998-04-27	COMPOSICAO ADESIVA, E, USO DA MESMA
<input checked="" type="checkbox"/>	AU7219998A1	1998-11-24	1998-04-27	HARDENER FOR HARDENING SILICATE SOLUTIONS
<input checked="" type="checkbox"/>	AU7219798A1	1998-11-24	1998-04-27	ADHESIVE COMPOSITION
<input checked="" type="checkbox"/>	AU7219698A1	1998-11-24	1998-04-27	SUSPENSIONS WITH HIGH STORAGE STABILITY, COMPRISING AN AQUEOUS SILICATE SOLUTION AND A FILLER MATERIAL
<input checked="" type="checkbox"/>	AT0206695E	2001-10-15	1998-04-27	WAESSRIGE SILIKATLOESUNG UND FUELLSTOFF ENTHALTENDE SUSPENSIONEN MIT HOHER LAGERSTABILITAET
34 family members shown above				

Other Abstract
Info:



THOMSON

CHEMABS 129(26)346411A CHEMABS 129(26)346485C CHEMABS 129(26)346496G DERABS C1998-594930 DERABS C1998-594931 DERABS C1998-594932



Nominate this for the Gallery...

Subscriptions | Web Seminars | Privacy | Terms & Conditions | Site Map | Contact Us | Help

Copyright © 1997-2007 The Thomson Corporation

SUSPENSIONS WITH HIGH STORAGE STABILITY, COMPRISING AN AQUEOUS SILICATE SOLUTION AND A FILLER MATERIAL, COMPOSITIONS CONTAINING THEREOF AND USING

Publication number:	HU0001904 (A2)	Also published as:	
Publication date:	2000-11-28		□ HU0001904 (A3)
Inventor(s):	HOWARTH IAN MAURICE [GB]; OSINGA THEO JAN [NL]		□ WO9849118 (A1)
Applicant(s):	CROSFIELD LIMITED, WARRINGTON, CHESHIRE		□ ZA9902113 (A)
			□ ZA9803696 (A)
			□ ZA9803695 (A)
Classification:			more >>
- international:	C04B14/04; C04B14/06; C04B28/26; C08L97/02; C09D1/02; C09J1/02; C09K8/05; D21H17/63; D21H27/30; C04B14/02; C04B28/00; C08L97/00; C09D1/00; C09J1/00; C09K8/02; D21H17/00; D21H27/30; (IPC1- 7): C04B28/26; C04B14/04; C04B22/00; C04B22/06; C09J1/02; C09K7/04; C09K17/12; D21H17/63		
- European:	C04B14/04; C04B14/06C; C04B28/26; C08L97/02; C09J1/02; C09K8/05		
Application number:	HU20000001904 19980427		
Priority number(s):	GB19970008831 19970430; WO1998GB01226 19980427		

Abstract not available for HU 0001904 (A2)

Abstract of corresponding document: **WO 9849118 (A1)**

Hardener for hardening silicate solutions comprising a silicate providing compound, capable of providing silica in amorphous or dissolved form in a silicate solution. Said silicate providing compound in the selected form amorphous silica and amorphous metal silicate. Further a silicate solution to be hardened, a method for hardening such a silicate solution and a hardened silicate material which can thus be obtained are described.

Data supplied from the esp@cenet database — Worldwide

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 28/26, 22/06, 22/00	A1	(11) International Publication Number: WO 98/49118 (43) International Publication Date: 5 November 1998 (05.11.98)
(21) International Application Number: PCT/GB98/01228 (22) International Filing Date: 27 April 1998 (27.04.98) (30) Priority Data: 9708831.4 30 April 1997 (30.04.97) GB (71) Applicant (for all designated States except US): CROSFIELD LIMITED [GB/GB]; Bank Quay, Warrington, Cheshire WA5 1AB (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): OSINGA, Theo, Jan [NL/NL]; Bemelerweg 50, NL-6267 AN Cadier en Keer (NL). (74) Agents: COLLINGWOOD, Anthony, Robert et al.; ICI Group Intellectual Property, P.O. Box 11, The Heath, Runcorn, Cheshire WA7 4QE (GB).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: HARDENER FOR HARDENING SILICATE SOLUTIONS (57) Abstract Hardener for hardening silicate solutions comprising a silicate providing compound, capable of providing silica in amorphous or dissolved form in a silicate solution. Said silicate providing compound in the selected form amorphous silica and amorphous metal silicate. Further a silicate solution to be hardened, a method for hardening such a silicate solution and a hardened silicate material which can thus be obtained are described.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Title: Hardener for hardening silicate solutions.

The present invention relates to hardeners for hardening silicate solutions.

In the state of the art, silicate solutions can be hardened by the addition of inorganic acids, organic acids or aluminate
5 to the silicate solutions. By addition of such components, the silicate solution hardens virtually instantaneously, however resulting in a relatively brittle product with too little inherent strength and durability.

Furthermore, it is essential in many applications, that
10 the hardening process is delayed for a predetermined period, allowing the mixture to be prepared before use, e.g. by mixing with other components which have to be transformed or shaped into a hard form, e.g. in foundries or before being sprayed onto surfaces to form a protective layer or before pumping into
15 the ground e.g. for waste fixation or grouting.

In an alternatively known technique, specially selected esters are added to silicate solutions, which hydrolyse in water, thus releasing acids, which harden the silicate solution in a slower and more controlled way. However the organic salts
20 and the alcohols formed during the hydrolysis of the expensive esters used for hardening, dilute the hardened system and weaken the bonding produced during the hardening of the silicate. Furthermore gases are generally slowly released that can cause smell, be toxic, or even form explosive gas mixtures in air
25 and consequently can not be applied in many applications for safety or environmental reasons.

Surprisingly, it has now been found that silica providing compounds, capable of providing silica in amorphous or dissolved form in a silicate solution are excellent hardeners for such
30 silicate solutions. It is known per se that by the addition of amorphous silica to a silicate solution, the molar ratio $\text{SiO}_2/\text{M}_2\text{O}$ of the silicate solution, M being an alkali metal or ammonium, can be increased.

Silicate solutions can be obtained from the market with
35 $\text{SiO}_2/\text{M}_2\text{O}$ molar ratios up to 3.3. To increase said ratio, amorphous silica is added and a solution with an $\text{SiO}_2/\text{M}_2\text{O}$ molar ratio of

4.0 can be obtained. The person skilled in the art is however aware of the fact that addition of more silica will lead to unwanted gelling of the silicate solution. The gelling point of the silicate solutions are at a $\text{SiO}_2/\text{M}_2\text{O}$ molar ratio of about
5 4.0 - 4.3, depending on the silicate content of the solution. Because of the gelling, further addition of silica has not been practised nor explored. It has now been found, that the addition of silica, or another reactive silica providing compound, see below, i.e. beyond the gelling point of the silicate solution,
10 leads to perfect hardening of the solution. Surprisingly, the reaction continues in the gel phase. This can be observed as the white silica particles, still present in the gel making the gel opaque, disappear in time, turning the soft gel into translucent hard gel, which finally after drying can become
15 a hard glass type product. It was found, that this reaction can continue until a molar ratio $\text{SiO}_2/\text{M}_2\text{O}$ (M being either sodium, potassium, lithium or ammonium) is reached in the gel of above 5.5. The maximum molar ratio which can be reached depends on time and temperature and will reach levels of around 7 at
20 slightly elevated temperatures already, as can be determined by those skilled in the art.

Furthermore, the hardening of the silicate solution with a hardener according to the present invention takes place gradually. The instantaneous hardening with known compounds
25 of the state of the art can therefore be avoided, leading to a hardened silicate solution not being brittle, but being very hard and of glassy consistency. By varying the amount of hardener according to the present invention added to the silicate solution, the reaction time needed for hardening can also be
30 varied. Thus, use of a hardener according to the present invention has the advantage of controlling the hardening time and of improving the quality of the hardened product.

Silica in amorphous form slowly dissolves in the silicate, thus acting as an acid, neutralizing the silicate and
35 consequently forming a gel which hardens in time. This is the case when sufficient amorphous silica is mixed in pure silicate liquors, giving a gel, but also when sufficient amorphous silica is mixed in suspensions comprising other ingredients like a filler material. The hardened product obtained when mixing

amorphous silica in silicate suspensions provided superior density, hardness and minimum permeability.

Consequently it was found, that amorphous silica or an amorphous alkali metal silicate form ideal hardeners, being
5 again completely inorganic and completely safe with respect to humans and the environment. It also further reduces the flammability and increases the solid content of the product obtained after hardening. An additional benefit is, that the hardened solution, using sufficient amorphous silica forms a
10 neutralised solid phase with superior adhesion and filling properties, which is very strong and substantially insoluble in water.

In the present application the silicate solutions can also comprise a filler, i.e. be a suspension.

15 Silicate solutions, suspensions comprising a hardener according to the invention are therefore suitable for applications, e.g. adhesion applications, where weatherproof properties are required, such as outside applications, construction of buildings for bonding bricks of outside walls, bonding leather
20 to be used outside like shoe soles etc. or for bonding wood for outside purposes. By using silicate solutions, suspensions hardened with the hardener according to the invention buildings, homes etc could be manufactured based on paper or other cellulosic material like woodfibres etc still having weatherproof
25 properties. Also bricks could be adhered together with such hardened solutions, no longer needing any mortar and associated drying time.

It was found, that the rate of hardening of the silicate solutions according to the invention, using amorphous silica
30 can be influenced by the choice of amorphous silica and by the amount of amorphous silica used. The use of silicas with a higher rate of dissolution in alkaline aqueous solutions increases the hardening rate.

It is therefore possible to control the hardening (setting)
35 rate by choosing the type of silica, the optimum concentration and the temperature, as can be carried out by a person skilled in the art. The hardener system should be mixed in the solution shortly before use.

As a hardener, also an amorphous metal silicate can be

used. Addition of such a compound results in a spacial configuration change of the silicate in the solution by alteration of the molar $\text{SiO}_2/\text{M}_2\text{O}$ ratio thereof. Suitable metal silicates are preferably those which do not readily dissolve
5 in the silicate solution to be hardened, like e.g. magnesium silicate, calcium silicate or aluminium silicate.

Preferably, the silica providing compound is chosen from the group, consisting of amorphous silica, and amorphous metal silicate that do not readily dissolve in the silicate solution.
10 The metal silicates are preferably chosen from the group, comprising magnesium silicate, calcium silicate and aluminium silicate. These silicates do not readily dissolve in the silicate solution and therefore give rise to a gradual hardening process of the silicate solution.

15 The invention also relates to a silicate solution to be hardened, comprising a hardener according to the invention, wherein said silicate solution has a silicate content of at least 10% by weight, and preferably at least 20% by weight. A hardening solution is intended to encompass a solution, or
20 suspension, comprising the hardener according to the present invention and a silicate solution. The hardener according to the invention functions very well in hardening silicate solutions having a silicate content of at least 10% by weight, and even better when the silicate content is at least 20% by weight.
25 The higher the silicate content in the solution, the harder the hardened phase obtained.

The $\text{SiO}_2/\text{M}_2\text{O}$ molar ratio of these soluble silicates can vary from 1.0 to around 4.0 and for lithium silicate even higher. All silicate solutions are alkaline, but the alkalinity decreases
30 with increasing molar ratio. Consequently less hardener is needed to harden the solution. Furthermore silicate solutions with higher molar ratios are safer in handling, which is demonstrated by the following safety classification of the standard silicate solutions as offered on the market.

35

<u>Molar Ratio</u>	<u>Solutions offered</u>	<u>Classification</u>
<u>SiO₂/M₂O:</u>	<u>on the market as:</u>	<u>in Europe (Safety):</u>
1.0	Metasilicate	Corrosive
2.0	"Alkaline" Silicate	Highly Irritant
5	(or: "Alkaline waterglass")	
3.3	"Neutral" Silicate	Not classified
as	(or: "Neutral waterglass")	unsafe

The preferred SiO₂/M₂O ratio for most applications is therefore above 2.6 and more preferably 3.3 and higher for safety reasons. As is outlined above, it is preferred to maximize the SiO₂ content and consequently also the SiO₂/M₂O ratio to minimize the amount of hardener required.

The amount of hardener required is highly influenced by the SiO₂/M₂O molar ratio of the silicate, as for higher molar ratios less hardener is needed for neutralization. Therefore, advantageously the SiO₂/M₂O molar ratio of the aqueous silicate solution to be hardened, M being an alkali metal or ammonium, is comprised between 1 - 4.5, preferably between 2 - 4.2 and most preferably between 2.6 - 4.2.

For many applications, it is advantageous to incorporate filler material in the silicate solution to be hardened. As filler material, zeolites as zeolite 4A, zeolite P, zeolite X and zeolite Y, fine particulate or fibres amorphous inorganic material being relatively inert in an alkaline aqueous solution, like amorphous alkali metal aluminosilicate, a fine particulate of graphite or carbon black or mixtures thereof can be used.

It is advantageous when the filler material has an average particle size between 0.8 - 15 µm with a specific weight of below 2.75 kg/l. It is however to be noted that filler material with other properties, i.e. with a smaller particle size, may be suitable as well, depending on the intended use of the hardening solution.

Preferably the filler material comprises a zeolite, in particular of the P-type.

The present invention further relates to a method for hardening a silicate solution, wherein a hardener according to the present invention is added to the silicate solution in an amount exceeding the amount of hardener, needed to gel the

solution.

The preferred amount of hardener can be either calculated or predetermined by those skilled in the art. The best results with respect to hardness are obtained, when the maximum amount of hardener, i.e.: reactive (amorphous) silica is added, which can react with the silicate used under the conditions applied in the application, which can be observed as the opaque amorphous silica then has disappeared. This will generally be reached, when the final molar ratio $\text{SiO}_2/\text{M}_2\text{O}$ of the silicate present in the gel is 4.4 - 5.5 at ambient temperature, but can reach higher values of up to 7, when the hardening takes place at elevated temperatures.

As outlined above, by adding a hardener according to the present invention, amorphous silica is added to the silicate containing solution, leading to an increase of the $\text{SiO}_2/\text{M}_2\text{O}$ ratio which results in gelling and subsequently, to hardening of the solution. The gelling point of the silicate solutions upon adding hardener lies around 4.1 - 4.3. Hardening takes place at higher molar ratios.

The present invention will now be illustrated with the following examples.

EXAMPLES

Materials used :

25

A.	Commercial name	: Crystal 0070 (Crosfield Eijsden (NL))
	Product	: Neutral sodium-silicate liquor
	Dry solid content	: 35.06 %
	SiO_2 content	: 26.81 %
30	Na_2O content	: 8.25 %
	Density (20 °C)	: 1355 g/l
	Viscosity	: 51 cP

C.	P-type zeolite in dry powder form	
35	Commercial name	: Zeocros CG180 (Crosfield Eijsden)
	Dry solid content*)	: 90 %
	Particle size **)	: 0.7 - 3 micrometer
	Average particle size **)	: 0.92 micrometer

D50 : 1.22 micrometer
Effective density***) : 2480 g/l.

L Lucilite.

5 A commercially available, synthetically produced amorphous Silica (hydrogel), marketed and produced by Crosfield, Warrington, UK.
Dry Solid content *) : 34.78 %

10 M. Gasil HP 250

A commercially available amorphous Silica, synthetically produced and marketed by Crosfield, Warrington, UK.
Dry Solid content *) : 93.49 %
Average Particle size: 4.8 - 6.2 micrometer (Mastersizer)

15

N. Microsil ED

A commercially available amorphous Silica, synthetically produced and marketed by Crosfield, Warrington, UK.
Dry Solid content *) : 89.37 %

20

Q. Stabifix Super

A commercially available amorphous Silica, synthetically produced and marketed by Crosfield, Warrington UK.
Dry Solid content *) : 94.6 %

25 Average Particle size: 10.3 maximum micrometer (Mastersizer)

*) Measured by heating at 800 °C during 30 minutes

**) Measured by the sedimentation technique using

30 Sedigraph type 5100, marketed by Micromeritics

***) Measured by immersion in water.

EXAMPLE 1

Addition of amorphous Silica to a neutral Sodium-silicate liquor.

35 Materials used:

	Material Nr.:	Dry Solid content (wt.%)
Neutral Sodiumsilicate liquor	A	35.06
Amorphous Silica: Lucilite	L	34.78

Amorphous Silica: Gasil HP250	M	93.49
Amorphous Silica: Microsil ED	N	89.37
Amorphous Silica: Stabifix Super	Q	94.6

5 Neutral silicate liquor (A) was introduced into a beakerglass of 600 ml.

A range of suspensions was made in which varying quantities of silica were added under intensive stirring to the silicate liquor.

10 It was not possible to produce suspensions adding more than approximately 15 % by weight on a dry basis of silica.

Suspensions Produced and behaviour during Storage:

(The SiO₂ and Sodiumsilicate contents of the suspensions are
15 expressed on bone dry basis)

Material	:	L				M			N			Q		
Sample Nr.	:	L1	L2	L3	L4	M1	M2	M3	N1	N2	N3	Q1	Q2	Q3
SiO ₂ (wt. %)	:	4.4	7.8	10.5	12.7	4.7	9	12.9	4.7	9	12.8	4.7	9	12.9
20 Silicate (wt.%)	:	31	27	25	22	33	32	30	33	32	30	33	32	30
Gelling Time(h)	:	<1/2	<1/2	<1/2	<3/4	15	<15	<15	>48	24	20	15	<15	<<15
Gel type, 1 day')	:	s	h	h	mh	l	s	s	l	s	s	l	s	h
Gel type, 2 days	:	s	h	h	h	l	s	s	l	s	h	l	s	h
Gel type, 4 days	:	s	h	h	h	l	h	h	s	h	h	l	h	h
25 Gel appearance')	:	t	t	t	o	-	g	g	-	-	t	g	g	g

*) After 1 day, the gel was assessed visually and after 1,2 and 4 days on strength by pressing a rod manually into the gel and assessing the pressure needed.

30 Following symbols were used to characterize the gel:
l = liquid; s = very-soft; mh = medium-hard and h = hard.
t = translucent; g = greyish; o = opaque

35 Summarizing:

Material L (Lucilite) is a hydrogel and most soluble and most reactive, resulting in fastest and most efficient gelling. The other silicas also show different gelling efficiencies. It was observed, that at increasing silica content gelling is
40 more efficient and the gel obtained becomes harder.

It can be assumed, that the silica dissolution process

for Material L, being highly reactive will have reached its end point within 1 day, while the other silicas were still reacting further.

Sample L4 shows, that at an apparent excess level of silica the gel becomes opaque and again softer. It was concluded from this, that there is an optimal silica addition level giving maximum hardness around the 10 % Silica level. This means 40 wt.% relative to the neutral silicate (Total effective Molar Ratio: $\text{SiO}_2/\text{Na}_2\text{O}$, then being around 4.7).

10

EXAMPLE 2, 3 and 4

Addition of amorphous Silica to a neutral Sodium-silicate liquor at 50 °C. and 80 °C

In order to demonstrate the influence of temperature on the gelation time, suspensions of Silica in a neutral Sodium-silicate liquor were produced at 50 °C and at 80 °C.

Procedure:

A mortar, which was preheated at 50 °C for Examples 2 and 3 or at 80 °C for Example 4, neutral Sodium-silicate liquor (Material A) was added and brought to the same temperature, Silica was subsequently added and shortly milled in order to realize fast mixing.

The suspension obtained was quickly transferred into a beakerglass of 250 ml kept at 50 °C for Examples 2 and 3 and at 80 °C for Example 4 in a waterbath.

Materials used:

Example Nr.	:	2*)	3**)	4**)
30 Material (Silicate)	:	A	A	A
Silicate Liquor (g)	:	100	100	100
Silica Material Nr.	:	L	M	M
Silica (as is) (g)	:	28.75	10.7	10.7
Storage Temperature (°C)	:	50	50	80
35 Start of gelling (min)***)	:	2	10	3

*) Example 2 is based on the same raw materials and has the same composition as sample L2 of Example 1, which was tested at room temperature (approx. 20 °C).

Gelling of sample L2 at room temperature started after approximately 30 minutes.

5 ") Examples 3 and 4 are based on the same raw materials and have the same composition as sample M2 of Example 1, which was also tested at room temperature. Gelling of sample M2 at 20 °C started very slowly and a real start point could not be defined (after several hours).

10 ") Gelling assessment at 50 °C and 80 °C:
Gelling was visually observed as well as by regularly assessing the strength needed to enter a glass rod in the gelling suspension.

Summarizing:

1. Increasing the storage- (or "curing"-) temperature
15 decreases the time needed for gelling or solidifying (or: "curing" or hardening").
2. Addition of amorphous silica offers an excellent means to gel (or "cure" or "harden") a silicate liquor.
- 20 3. Curing silicate liquors using amorphous silica also renders the hardened product less soluble in water, creating a more permanent "cure" even when in contact with water.

EXAMPLES 5-9

Addition of amorphous Silica to suspensions of zeolite of a
25 **P-type in a neutral silicate liquor.**

Procedure:

A suspension of 15 % by weight of zeolite in neutral Sodiumsilicate liquor was prepared, following the procedure as in EXAMPLE 1 using the same beakerglass and following
30 materials:

Zeolite in silicate suspension:

Silicate liquor (g) : 500
(Material A)
35 Zeolite powder (g) : 100
(Material C)
Zeolite content (wt.%): 15
(Bone dry basis)

This suspension was split up in 120 g portions to which amorphous silica was added at room temperature in a mortar.

After intensive milling in the mortar, the samples were gathered in small beakerglasses for assessment of the gelling process.

The following tests were carried out:

EXAMPLE Nr.	:	5	6	7	8	9
10 Zeolite suspension (g)	:	120	120	120	120	120
Amorphous Silica:						
- Material Nr.	:	L	L	L	M	M
- weight (as is) (g)	:	14.4	28.8	43.1	5.37	10.7
Final Composition Slurry						
15 Silicate (dry basis) (wt.%)	:	26.1	23.6	21.5	28.0	26.8
Zeolite (dry basis) (wt.%)	:	13.4	12.1	11.0	14.4	13.8
Silica (dry basis) (wt.%)	:	3.7	6.7	9.2	4.0	7.7
Water content (wt.%)	:	56.8	57.6	58.3	53.6	51.7
20 Gelling *) :						
- gelling start (min.)	:	30	30	30		
- after 1 day	:	s.g	g	h	s.g	h
- after 2 days	:	s.g	h	h	s.g	h
- after 3 days	:	s.g.	h	h	s.g	h

25 *) Gelling is specified as: s.g.= soft gel; g = gel; h = hard.

The gelled suspensions of EXAMPLES 6, 7 and 9 were harder than those of the gelled suspensions L2, L3, L4, M2 and M3 of EXAMPLE 1, showing the additional strengthening resulting from the zeolite additionally present in the suspension.

Exerting a similar force on a thin glass rod in hardened (cured) gels containing 11 - 14.4 wt. % additional zeolite reduced the penetration by a factor of roughly 3 - 4.

C L A I M S

1. Hardener for hardening silicate solutions comprising a silica providing compound, capable of providing silica in
5 amorphous or dissolved form in a silicate solution.
2. Hardener according to claim 1, characterized in that the silica providing compound is selected from the group, comprising amorphous silica and an amorphous metal silicate.
- 10 3. Hardener according to claim 2, characterized in that the amorphous metal silicate is selected from the group, comprising magnesium silicate, calcium silicate and aluminium silicate.
- 15 4. Silicate solution to be hardened, comprising a hardener according to one or more of the preceding claims, wherein said silicate solution has a silicate content of at least 10% by weight, preferably at least 20% by weight.
- 20 5. Silicate solution to be hardened, comprising a hardener according to one or more of claims 1-3, wherein said silicate solution has an $\text{SiO}_2/\text{M}_2\text{O}$ molar ratio, M being an alkali metal or ammonium, being comprised between 1 - 4.5, preferably between 2 - 4.2 and more preferably between 2.6 - 4.2.
- 25 6. Silicate solution to be hardened, comprising a hardener according to one or more of claims 1-3, wherein said silicate solution comprises a filler material.
- 30 7. Silicate solution according to claim 6, characterized in that the filler material has an average particle size of 0.8 - 15 μm and a specific weight of below 2.75 kg/l.
8. Silicate solution according to claim 6 or 7, characterized
35 in that the filler material comprises a zeolite.
9. Silicate solution according to claim 8, characterized in that the zeolite is of the P-type.

10. Method for hardening a silicate solution, wherein a hardener according to claim one or more of claims 1-3 is added to the silicate solution in an amount exceeding the amount of hardener needed to gel the solution.

5

11. Method according to claim 10, characterized in that the amount of hardener added to the silicate solution is selected such that the $\text{SiO}_2/\text{M}_2\text{O}$ molar ratio, M being an alkali metal or ammonium, of the silicate solution is increased to between 5-7.

10

12. Method according to claim 11, characterized in that the amount of hardener added to the silicate solution is selected such that the $\text{SiO}_2/\text{M}_2\text{O}$ molar ratio, M being an alkali metal or ammonium, of the silicate solution is increased to between 4.4 -

15 5.5.

13. Hardened silicate material obtainable by hardening a silicate solution according to one or more of claims 4-9.

20

INTERNATIONAL SEARCH REPORT

Int. l. Application No
PCT/GB 98/01228

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C04B28/26 C04B22/06 C04B22/00		
According to International Patent Classification(IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 C04B		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 94 04355 A (VETROTECH AG) 3 March 1994 see page 3, line 25-29 ---	1,2
X	DATABASE WPI Week 8510 Derwent Publications Ltd., London, GB; AN 85-059657 XP002074071 & JP 60 016 856 A (NIPPON CHEM IND CO) see abstract ---	1,3
A	EP 0 458 504 A (ACHESON INDUSTRIES INC.) 27 November 1991 see claim 1 ---	6-8
A	US 3 920 578 A (P. C. YATES) 18 November 1975 see claim 1 ---	1,2
-/-		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
Date of the actual completion of the international search 10 August 1998		Date of mailing of the international search report 19/08/1998
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl. Fax: (+31-70) 340-3016		Authorized officer Daeleman, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/01228

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Week 7420 Derwent Publications Ltd., London, GB; AN 74-37426v XP002074072 & JP 49 015 941 B (NIPPON CHEM IND CO) see abstract</p> <p>---</p>	1,2,10, 13
A	<p>DATABASE WPI Week 7907 Derwent Publications Ltd., London, GB; AN 79-12741b XP002074073 & JP 54 001 325 A (AOYAMA) see abstract</p> <p>---</p>	1,2,6, 10,13
A	<p>PATENT ABSTRACTS OF JAPAN vol. 095, no. 004, 31 May 1995 & JP 07 010632 A (Y. MASAHIITO, ET AL.), 13 January 1995 see abstract</p> <p>---</p>	1,3
A	<p>WO 90 12834 A (C. LUNDSTROEM) 1 November 1990 see claim 1</p> <p>---</p>	1,2
A	<p>PATENT ABSTRACTS OF JAPAN vol. 018, no. 575, 4 November 1994 & JP 06 211557 A (SEKISUI CHEM CO), 2 August 1994 see abstract</p> <p>---</p>	1,3,6,13
A	<p>EP 0 100 848 A (DYNAMIT NOBEL AG) 22 February 1984 see claim 1</p> <p>---</p>	1,2
A	<p>US 3 492 137 A (R. K. HER) 27 January 1970</p> <p>-----</p>	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/01228

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9404355 A	03-03-1994	AU 4556693 A EP 0620781 A FI 941624 A JP 7500310 T LT 3204 B LV 11049 A LV 11049 B NO 941272 A,B, US 5565273 A	15-03-1994 26-10-1994 08-04-1994 12-01-1995 27-03-1995 20-02-1996 20-04-1996 08-04-1994 15-10-1996
EP 458504 A	27-11-1991	JP 4025570 A JP 7082821 B US 5147460 A	29-01-1992 06-09-1995 15-09-1992
US 3920578 A	18-11-1975	AT 302146 B BE 734385 A DE 1929712 A FR 2010783 A JP 48033152 B LU 58839 A NL 6908896 A	15-08-1972 17-11-1969 12-03-1970 20-02-1970 12-10-1973 30-10-1969 16-12-1969
WO 9012834 A	01-11-1990	AU 5672390 A	16-11-1990
EP 100848 A	22-02-1984	DE 3229339 A DE 3303409 A JP 1706455 C JP 3075691 B JP 59052026 A US 4522652 A	09-02-1984 02-08-1984 27-10-1992 03-12-1991 26-03-1984 11-06-1985
US 3492137 A	27-01-1970	NONE	